



Heimerle + Meule Group



Cookson Precious Metals Ltd,
59-83 Vittoria Street, Birmingham, B1 3NZ, UK



Cookson Drijthout BV
Keienbergweg 12 1101 GB Amsterdam

Device Name: MATTIBEL G

Device Type: Deep Yellow: Inlay Gold
Casting Alloy

Indications: TYPE 1: For low stress bearing single-tooth fixed
protheses, e.g., veneered or unveneered one-surface
inlays, veneered crowns

Free from Be, Cd, Ni, and Si.

Intended Use: Fabrication of custom-made dental restorations

Intended Patients: Any (no restriction on patient characteristics)

Intended Users: Dental laboratory technicians.

**There are no specific contraindications, warnings, or precautions for patients,
though see composition if patient allergies are known or suspected.**

There are no special storage requirements for this material.



g

LOT

--

REF

ZBG 000

Technical Data

Density	16.0 g/cm ³	
Composition	Au 78.3% Ag 14.9% Cu 6.5% Others <1.0% Zn	
Melting Range	925 - 945 °C	
Elongation	80%	As-cast condition
0.2% Proof Stress	150MPa	
Casting Temperature	1075°C	
Casting Ring Pre-Heat	700°C for 40 minutes.	
Recommended Solder	Mattiflo 830Y	
Flux	Tenacity 125	
Typical Applications	Class 4 or 5 inlays	

Additional Information

Disposal / Re-Use Considerations:	Clean scrap can be reused to make further restorations, however alloys that have been used on patients should not be reused to minimize contamination risk. Once appropriately cleaned, precious metal alloys may be sent for recycling.
In the event of a defective device	Contact Cooksongold on +441212338170. If the defect has only become apparent after the alloy has been used on a patient, then also contact the competent authority of the Member State in which the patient is established (refer to https://ec.europa.eu/health/md_sector/contact_en)
Summary of Safety and Clinical Performance (SSCP)	The Summary of Safety and Clinical Performance (SSCP) is available on request and can also be found at https://ec.europa.eu/tools/eudamed by searching for the Basic UDI-DI 5057531 ALLOYTL (when the website is operational).

DIRECTIONS FOR USE

WAXING

A minimum wax thickness of 0.3 mm is recommended.

Sprue each unit individually with 2.5 mm wax rods. If using reservoir bars, sprue diameter can be reduced to 1.5 mm. Vent rods should be 1 mm if used.

Avoid sharp joints and ensure all shoulders and edges are well rounded. Stress relieve the wax pattern in water at 32 °C for 5 - 10 minutes.

INVESTMENT

Most investments suitable for gold casting alloys will give excellent results., this includes graphite-based powders. Pouring the investment under vacuum and using a debubbleiser will assist in producing a smooth surface finish.

BURN OUT AND PRE - HEAT

Follow normal procedures for wax burn out and heat the investment according to the manufacturer's instructions. Heat soak the casting ring for a minimum of 40 minutes at 700°C. Time necessary to successfully heat soak the casting ring increases with size.

CASTING

All surplus/scrap metal can be successfully re-melted provided all traces of investment have been removed and the metal is clean. It is strongly advised to add approximately 1/3rd new metal to each melt.

A little Tenacity 125 flux added to the melt immediately before casting will improve overall cleanliness and will help to prevent oxidation. This is especially important when adding scrap metal. Ensure the alloy is fully liquid and spinning before casting. The time taken to reach both melting and casting temperature must be kept to a minimum and the alloy cast promptly if overheating is to be prevented.

As well as miscasts and porosity, over heating can result in the crown "blackening" once fitted., To avoid this, oxy - propane torches must be correctly adjusted, and Induction furnaces calibrated regularly.

CLEANING

Break out the metal and clean by brushing or by sand blasting with non-recycling aluminium oxide after which an acid pickle will ensure total cleanliness of the casting. Finally prepare the surface of the metal with a proprietary stone kept solely for use on **MATTIBEL G** and polish to a high lustre using brushes and rouge.

MATTIBEL G is not suitable for heavy milling.

INDICATIONS

MATTIBEL G is a medium soft casting alloy with a rich yellow colour.

Its physical properties make the alloy suitable ONLY for use in class 4 and 5 inlay sites. In these positions, the excellent colour and finish of the alloy is ideal.

SOLDERING

Good results can be achieved by using Mattiflo 830Y and a freshly prepared paste of Tenacity 125.

If the alloy is being soldered to a dissimilar alloy ie Matticraft C, it is essential that adequate preheating and complete cleanliness is maintained at all times.

Caution: *Suitable protective clothing and the wearing of safety glasses is recommended when melting this product.*

No special storage requirements